

<b>Nominal Dimensions</b>	12" x 12" x 0.100" (2.5 mm) Tiles, 55 per carton 24" x 24" x 0.100" (2.5 mm) Tiles, 10 per carton
<b>Finish</b>	Smooth, No Factory Finish
<b>ASTM F1066 - Vinyl Composition Tile</b>	Exceeds Requirements
<b>ASTM E648 (NFPA 253) - Critical Radiant Flux</b>	Passes; Class 1, $\geq 0.45$ W/cm <sup>2</sup>
<b>ASTM E662 (NFPA 258) - Smoke Density</b>	Passes; $\leq 450$
<b>ASTM D2047 - Static Coefficient of Friction</b>	$\geq 0.5$
<i>ADA Standards for Accessible Design states the floor surface shall be stable, firm and slip resistant. Our test results utilize the James Machine as described in D2047 and as described in UL410 for floor covering materials (FCM) utilizing a leather foot under dry conditions. Maintenance processes and commonly utilized site applied finishes, polishes and other sealers to maintain resilient flooring products will change the walking surface and ultimately the Static Coefficient of Friction.</i>	
<b>ASTM F970 - Static Load Resistance</b>	Passes; $< 0.005$ " Indentation @ 250 psi
<b>ASTM F970 - Static Load Resistance (Modified)</b>	Passes; $\leq 0.005$ " Indentation @ 5000 psi
<i>ASTM F970 testing at loads above 250 psi is outside the scope of the test method. Since testing is conducted on flooring product alone, our stated results do not take into consideration chosen adhesive, any utilized underlayments and/or substrates or subfloors. These results should not be construed as an indicator of installed flooring performance.</i>	
<b>ASTM F925 - Chemical Resistance</b>	Excellent, Additional Chemicals Chart Available
<i>ASTM F925 testing is utilized to ensure flooring materials will stand up to certain household standard chemistries. Additional chemical resistance testing performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately.</i>	
<b>ASTM F2240 - Hardness</b>	Shore D; $\geq 65$
<b>ASTM D3389 - Abrasion Resistance</b>	Excellent, $\leq 1$ g loss after 1,000 cycles
<b>ASTM F2199 - Dimensional Stability</b>	Excellent, $\leq 0.020$ " per linear foot
<b>ASTM F1514 - Heat Stability</b>	Excellent, $\Delta E \leq 8$
<b>ASTM F1515 - Light Stability</b>	Excellent, $\Delta E \leq 8$
<b>ASTM F1914 - Residual Indentation</b>	Excellent, $\leq 8\%$ after 24 hour recovery
<b>Sustainability Information</b>	Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements NSF/ANSI 332 Platinum Certification Contains No Recycled Content
<b>Acclimation Time</b>	48 Hours
<b>Service &amp; Storage Temperature</b>	65° - 85° F

<b>Warranty</b>	20 Year Commercial
<b>Approved Adhesives</b>	Consult Traverse
<b>Technical Support</b>	<a href="mailto:info@traverseflooring.com">info@traverseflooring.com</a>